



T H E H A R R I S P R O D U C T S G R O U P
A L I N C O L N E L E C T R I C C O M P A N Y
 4501 Quality Place • Mason, OH 45040 U.S.A Tel: 513-754-2000 Fax: 513-754-6015

TECHNICAL SPECIFICATION SHEET

309LT1-1 FLUX CORED STAINLESS STEEL WELDING WIRE

STATEMENT OF LIABILITY- DISCLAIMER

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

APPLICATION:

Used to join dissimilar steels and materials of AISI 309 composition. It is also recommended for use as a first layer in a single or multilayer surfacing of non-alloy and low alloy steels to give a 304L deposit. By specifying low carbon content in this alloy, it's impossible to obtain resistance to inter granular corrosion due to carbide precipitation without the use of stabilizers such as Columbium or Titanium. This material is generally used with 100% CO₂ or mixture of Argon and CO₂, typically 75%-25% mixtures. Recommended wire stick out is 5/8"-3/4".

NOMINAL COMPOSITION:

Carbon	.04% max	Chromium	22-25%
Nickel	12-14%	Manganese	.50-2.5
Copper	50% max.	Silicon	1%
Phosphorus	.04% max	Sulfur	.03% max
Molybdenum	.50% max	Iron	Balance

Typical MECHANICAL PROPERTIES AS WELDED:

Yield Strength	57,000 psi
Elongation	30% min
Tensile Strength	87,000 psi

All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

Additional information available at our web site: www.harrisproductsgroup.com

7/99 DC



**RECOMMENDED WELDING PARAMETERS:
FCAW Parameters (DC Reverse Polarity) Electrode Positive**

<u>Wire Diameter</u>	<u>Welding Position</u>	<u>Joint Type</u>	<u>Plate Thickness</u>	<u>Amps</u>	<u>Volts</u>	<u>Deposition ipm</u>
.035	Flat	Butt	1/8"	70-90	25-27	12-16
.035	Flat	Butt	1/4"	120-130	26-29	10-14
.035	Flat	Fillet	1/4"	110-130	26-29	12-16
.035	Vertical up	Butt& Fillet	3/8"	70-90	22-25	6-10
.035	Horizontal	Butt	3/32"	100-120	24-27	12-16
.035	Overhead	Fillet	3/8"	150-200	26-28	8-12
.45	Flat	Butt	1/4"	180-200	29-32	12-16
.45	Flat	Fillet	3/8"	170-200	28-32	10-16
.45	Vertical up	Butt& Fillet	3/8"	110-140	21-24	4-8
.45	Horizontal	Butt	1/4"	150-180	26-30	10-16
.45	Overhead	Fillet	3/8"	150-200	26-28	10-14
1/16	Flat	Butt	1/4"	210-220	27-30	14-16
1/16	Flat	Fillet	3/8"	220-250	27-31	12-18
1/16	Vertical up	Butt& Fillet	3/8"	130-160	21-24	6-8
1/16	Horizontal	Butt	1/4"	150-200	26-30	10-16
1/16	Overhead	Fillet	3/8"	150-200	27-30	12-14

* All parameters are suggested as basic guidelines and will vary depending on joint design, number of passes and other factors.
SPECIFICATION COMPLIANCE: ANSI/AWS A5.22 & ASME SFA 5.22 E 309LT1-1

WARNING: PROTECT yourself and others. Read and understand this information.

FUMES AND GASES can be hazardous to your health.

ARC RAYS can injure eyes and burn skin.

ELECTRIC SHOCK can KILL.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the arc, or both, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- Do not touch live electrical parts.
- See American National Standard Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402.

All statements, information and data given are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind, expressed or implied.

Additional information available at our web site: www.harrisproductsgroup.com

7/99 DC